

„MEŽA UN KOKSNES PRODUKTU PĒTNIECĪBAS UN ATTĪSTĪBAS INSTITŪTS” SIA
VAT No. LV 43603022749
Dobeles iela 41, Jelgava, LV-3001, Latvia
Phone +371 63010605 * E-mail meka@e-koks.lv * Web www.e-koks.lv



Classification of reaction to fire in accordance with EN 13501-1:2018

Issue number: K47/2023

Date of issue: 09.05.2023.

Sponsor: Keflico A/S.

Address: Juelstrupparken 24, DK 9530 Stoevring, Denmark.
Reg. No. DK23980010.

Manufacturer and owner of classification report: Keflico A/S.

Prepared by: SIA “Meža un koksnes produktu pētniecības un attīstības institūts” (*Forest and Wood Products Research and Development Institute Ltd*).

Test performed at: SIA “Meža un koksnes produktu pētniecības un attīstības institūts” (*Forest and Wood Products Research and Development Institute Ltd*), “Pienavas katlu māja”, Pienava, Džūkstes pagasts, Tukuma novads, LV-3147, Latvia (*“Pienava heat plant”, Pienava, Džūkste parish, Tukums region, LV-3147, Latvia*).

Product name: Keflico Façade Lamellas – Solid Mahogany.

Laboratory involved in testing is accredited by the Latvian National Accreditation Bureau (LATAK) according to the standard LVS EN ISO/IEC 17025 under the terms of Latvian legislation with reg. No. T-316. Laboratory is a notified body with reg. No. NB 2040 under construction product regulation No. 305/2011.

Classification report refers only to these test objects. This classification report may not be reproduced otherwise than in full text, excepted with the prior written approval of the Forest and Wood Products Research and Development Institute

1. Introduction

This classification report defines the reaction to fire classification assigned to Keflico Façade Lamellas – Solid Mahogany in accordance with the procedures given in EN 13501-1:2018.

2. Details of classified product

2.1. General

Keflico Façade Lamellas – Solid Mahogany defined as solid wood cladding according standard EN 14915:2013.

2.2. Product description

- Product name: Keflico Façade Lamellas – Solid Mahogany.
- Manufacturer: Keflico A/S.
- Materials used for manufacturing:
 - Mahogany solid wood lamellas with cross-section dimensions 20 x 40 mm;
 - lamellas installed with CC distance 50 mm on wooden studs.

3. Test reports and test results in support of classification

3.1. Specific conditions

Not applicable

3.2. Test reports

Name of laboratory	Name of sponsor	Test reports	Test method
SIA „Meža un koksnes produktu pētniecības un attīstības institūts” Testing Laboratory	Keflico A/S	8072-1/2023	EN 13823:2020+A1:2022
SIA „Meža un koksnes produktu pētniecības un attīstības institūts” Testing Laboratory	Keflico A/S	8072-2/2023	EN ISO 11925-2:2020

3.3. Test results

Test method	Parameter	Number of tests	Results	
			Continuous parameter mean	Compliance parameters
EN 13823:2020+A1:2022	<i>FIGRA</i> _{0,2MJ} (W/s)	4	572.1	(-)
	<i>FIGRA</i> _{0,4MJ} (W/s)		572.1	(-)
	<i>THR</i> _{600s} (MJ)		89.1	(-)
	<i>LFS</i>		no	Compliant
	<i>SMOGRA</i> (m ² /s ²)		30.7	(-)
	<i>TSP</i> _{600s} (m ²)		64.8	(-)
	Flaming droplets <10s Flaming droplets >10s		(-) (-)	Compliant Compliant
EN ISO 11925-2:2020 Exposure time 30 s. Test duration 60 s.	Flame spread (Fs)	12	(-)	Compliant
	Ignition of filter paper		(-)	Compliant
	Flaming droplets/particles		(-)	Compliant
(-) not applicable				

4. Classification and field of application

4.1. Reference of classification

This classification has been carried out in accordance with clause 11 of EN 13501-1:2018.

4.2. Classification

Keflico Façade Lamellas – Solid Mahogany in relation to its reaction to fire behaviour is classified:

D

The additional classification in relation to smoke production is:

s2

The additional classification in relation to flaming droplets/particles is:

d2

The format of the reaction to fire classification for construction product excluding floorings and linings is:

Fire behaviour		Smoke production			Flaming droplets	
D	-	s	2	,	d	2

Reaction to fire classification: D-s2, d2

4.3. Field of application

4.3.1 This classification is valid for the following product end use applications:

Product primary is intended to use as cladding in buildings.

4.3.2. This classification is also valid for following product parameters:

- valid for product geometry as tested;
- valid only for solid Mahogany wood species as tested;
- valid only without additional coatings;
- valid for mounting with ventilated or non-ventilated air gap to substrate of any A1 or A2-s1,d0 with a minimum density of 525 kg/m³, and with the air gap constructed by wooden battens of class D-s2,d0 or better or any A1 or A2-s1,d0 product;
- valid for product mounting with air gap between product and substrate. Valid also for product mounting on substrates without air gap;
- valid for vertical and horizontal arrangements.

5. Limitations.

5.1. No restrictions on the duration of validity of this classification report as long as the product specifications remain unchanged.

5.2. This document does not represent type approval or certification of the product.

Prepared by



E. Bukšāns

(signature and name)

Reviewed by



K. Būmanis

(signature and name)

THIS DOCUMENT IS SIGNED BY SECURE ELECTRONIC SIGNATURE AND CONTAINS A TIME STAMP
 (Signature validity can be checked: <https://www.eparaksts.lv/en>)