

„MEŽA UN KOKSNES PRODUKTU PĒTNIECĪBAS UN ATTĪSTĪBAS INSTITŪTS” SIA
VAT No. LV 43603022749
Dobeles iela 41, Jelgava, LV-3001, Latvia
Phone +371 63010605 * E-mail meka@e-koks.lv * Web www.e-koks.lv



Classification of reaction to fire in accordance with EN 13501-1:2018

Issue number: K8/2025

Date of issue: 22.01.2025.

Sponsor: Keflico A/S.

Address: Juelstrupparken 24, DK 9530 Stoevring, Denmark.
Reg. No. DK23980010.

Manufacturer and owner of classification report: Keflico A/S.

Prepared by: SIA “Meža un koksnes produktu pētniecības un attīstības institūts” (*Forest and Wood Products Research and Development Institute Ltd*).

Test performed at: SIA “Meža un koksnes produktu pētniecības un attīstības institūts” (*Forest and Wood Products Research and Development Institute Ltd*), “Pienavas katlu māja”, Pienava, Džūkstes pagasts, Tukuma novads, LV-3147, Latvia (*“Pienava heat plant”, Pienava, Džūkste parish, Tukums region, LV-3147, Latvia*).

Product name: Keflico Design Panels – SONO.

The laboratory involved in testing is accredited by the Latvian National Accreditation Bureau (LATAK) according to the standard LVS EN ISO/IEC 17025 under the terms of Latvian legislation with reg. No. T-316.

The classification report refers only to these test objects. This classification report may not be reproduced otherwise than in full text, except with the prior written approval of the Forest and Wood Products Research and Development Institute

1. Introduction

This classification report defines the reaction to fire classification assigned to Keflico Design Panels – SONO in accordance with the procedures given in EN 13501-1:2018.

2. Details of classified product

2.1. General

Keflico Design Panels – SONO is defined as fire retardant-treated perforated pine plywood panelling for buildings. The product can be described by harmonized technical specification standard EN 13986:2004+A1:2015.

2.2. Product description

- Product name: Keflico Design Panels – SONO.
- Manufacturer: Keflico A/S.
- Materials used for manufacturing:
 - 12 mm fire retardant pine plywood;
 - veneered with alpi veneer or without;
 - perforation geometry:
 - 6 mm with distance cc 20 mm;
 - 8 mm with distance cc 20 mm;
 - sound dew 75 g/m²;
 - fire retardant lacquering system MAS2.
- Tested thickness: 12 mm.
- Tested colour: black, red and white.

3. Test reports and test results in support of classification

3.1. Specific conditions

Not applicable

3.2. Test reports

Name of laboratory	Name of sponsor	Test reports	Test method
SIA „ Meža un koksnes produktu pētniecības un attīstības institūts” Testing Laboratory	Keflico A/S	9667-3/2024	EN 13823:2020+A1:2022
SIA „ Meža un koksnes produktu pētniecības un attīstības institūts” Testing Laboratory	Keflico A/S	9667-4/2024	EN ISO 11925-2:2020
SIA „ Meža un koksnes produktu pētniecības un attīstības institūts” Testing Laboratory	Keflico A/S	10163-1/2025	EN 13823:2020+A1:2022
SIA „ Meža un koksnes produktu pētniecības un attīstības institūts” Testing Laboratory	Keflico A/S	10163-2/2025	EN ISO 11925-2:2020

Sampling for fire tests was done by DNV Business Assurance Denmark A/S (notified body NB 0527) at Kelico A/S Fabriksvej 12-14 7441 Bording Denmark (Test report No. 9667-3/2024 and 9667-4/2024) and Juelstrupparken 24, DK 9530 Stoevring, Denmark (Test report No. 10163-1/2025 and 10163-2/2025).

3.3. Test results

Test method	Parameter	Number of tests	Results	
			Continuous parameter mean	Compliance parameters
EN 13823:2020+A1:2022	$FIGRA_{0,2MJ}(W/s)$	3 ^{a)} 8 ^{c)}	74 ^{a)} 58 ^{c)}	(-) (-)
	$FIGRA_{0,4MJ}(W/s)$		74 ^{a)} 58 ^{c)}	(-)
	$THR_{600s}(MJ)$		4.4 ^{a)} 5.5 ^{c)}	(-)
	$LFS < edge\ of\ specimen$		yes ^{a; c)}	Compliant
	$SMOGRA(m^2/s^2)$		1 ^{a)} 3 ^{c)}	(-)
	$TSP_{600s}(m^2)$		20 ^{a)} 37 ^{c)}	(-)
	Flaming droplets <10s Flaming droplets >10s		(-) (-)	Compliant Compliant
EN ISO 11925-2:2020	Flame spread (Fs) ≤ 150mm	6 ^{b; d)}	yes ^{b; d)}	Compliant
Exposure time 30 s.	Ignition of filter paper		no ^{b; d)}	Compliant
Test duration 60 s.	Flaming droplets/particles		no ^{b; d)}	Compliant
(-) not applicable a) Tests results from test report No. 9667-3/2024; b) Tests results from test report No. 9667-4/2024; c) Tests results from test report No. 10163-1/2025; d) Tests results from test report No. 10163-2/2025.				

4. Classification and field of application

4.1. Reference of classification

This classification has been carried out in accordance with clause 11 of EN 13501-1:2018.

4.2. Classification

Keflico Design Panels – SONO in relation to its reaction to fire behaviour is classified:

B

The additional classification in relation to smoke production is:

s1

The additional classification in relation to flaming droplets/particles is:

d0

The format of the reaction to fire classification for construction product excluding floorings and linings is:

Fire behaviour		Smoke production			Flaming droplets	
B	-	s	1	,	d	0

Reaction to fire classification: B-s1, d0

4.3. Field of application

4.3.1 This classification is valid for the following product end-use applications:

Product primary is intended to be used as panelling in buildings.

4.3.2. This classification is also valid for the following product parameters:

- valid for product composition and geometry as tested;
- valid only for fire retardant pine plywood as tested;
- valid only for fire retardant lacquering systems as tested;
- valid only for perforation geometry as tested;
- valid for product mounting directly on substrates of reaction to fire class A1 and A2-s1,d0 having density at least 30 kg/m³ and thickness at least 20 mm;
- mounted on wood battens of reaction to fire class D-s2,d0 or better and any A1 and A2-s1,d0 battens if the air gap is filled with rock-fibre wool.
- valid for all colours.

5. Limitations.

5.1. No restrictions on the duration of validity of this classification report as long as the product specifications remain unchanged.

5.2. This document does not represent type approval or certification of the product.

Prepared by



E. Bukšāns

(signature and name)

Reviewed by



K. Būmanis

(signature and name)

THIS DOCUMENT IS SIGNED BY SECURE ELECTRONIC SIGNATURE AND CONTAINS A TIME STAMP
(Signature validity can be checked: <https://www.eparaksts.lv/en>)