



## Abachi

### Triplochiton scleroxylon

Application:	Mouldings, door panels and other panels, table top, furniture blocks, eaves, model building and saunas etc.
Family:	Sterculiaceae
Origin:	Ayous - Cameroun, Wawa - Ghana, Samba - the Ivory Coast.
About the tree:	Reaches a total height of up to 50 m and the bole may be up to 30 m long. The buttresses can reach up to 6 m of height. The trunk shape is cylindrical with a diameter of 100-240 cm.
Cutting:	Keflico stocks parallel sawn Abachi.
Quality:	No. 1 Common & Select.
Density:	380 kg/m <sup>3</sup> at 12 % moisture.
Moisture content:	Parallel sawn goods 10% (+/- 2%).
Thickness:	As per agreement.
Width:	150 mm and up.
Length:	215-600 cm.
Properties:	Sapwood is not clearly demarcated from the heartwood. The heartwood is whitish to pale yellow. Easily discoloured unless the tree is handled properly.
Working properties:	Easy workability. However, silicon deposits may affect operations.
Alternatives:	Aspen (Poplar).
Contact us:	Please contact our sales department tel. +45 9813 3544 or info@keflico.com.
Latest update:	09.02.2017

The information on this data sheet is for guidance only. We accept no liability for any inaccuracy or printing errors. This product is not FSC® or PEFC™ certified.

**Keflico A/S**  
 info@keflico.com  
 www.keflico.com  
 +45 9813 3544

**Støvring**  
 Juelstrupparken 24  
 DK-9530 Støvring

**Odense**  
 Bjerggårds Allé 2  
 DK-5240 Odense NØ

**Glostrup**  
 Naverland 1C, 1. sal  
 DK-2600 Glostrup



Miljømærket for ansvarligt skovbrug