



Western Red Cedar

Thuja plicata

Application:	Cladding and joinery.
Family:	Thuja plicata
Origin:	Canada.
About the tree:	Straight trunk with resin canals absent. The tree may grow to a height of 75 m.
Cutting:	Keflico stocks cladding in Western Red Cedar. This product is PEFC™ certified.
Quality:	No. 2 Clear only. A knot-free quality.
Density:	350 - 450 kg/m ³ at 12 % moisture.
Moisture content:	14 %
Thickness:	23 mm (7/8 x 6") kiln-dried, 52 mm (2 x 6") kiln-dried. 104 mm (4 x 6") air-dried.
Width:	150 mm
Length:	As per agreement.
Properties:	Narrow, yellowish/whitish sapwood. Pale wood, extremely durable outdoor due to its natural content of "Thuja Implimer" and fungicides. Aromatic scent – resistant to insect damage. Please note, the wood is not a Class 2 cladding due to low density.
Working properties:	Good machinability. Easily attached due to its softness.
Contact us:	Please contact our sales department tel. +45 9813 3544 or info@keflico.com.
Latest update:	09.02.2017

The information on this data sheet is for guidance only. We accept no liability for any inaccuracy or printing errors. This product is PEFC™ certified.

Keflico A/S
info@keflico.com
www.keflico.com
+45 9813 3544

Støvring
Juelstrupparken 24
DK-9530 Støvring

Odense
Bjerggårds Allé 2
DK-5240 Odense NØ

Glostrup
Naverland 1C, 1. sal
DK-2600 Glostrup



Miljømærket for ansvarligt skovbrug